



CORROSION CONTROL

Technical Datasheet

CARBONACEOUS BACKFILL



All the products are supplied in 25 kg multiwall paper sacks, packed 1000 kg per pallet and shrink cover wrapped.

Petroleum Coke

Petroleum coke suitable for deep bore holes where slurry pumping may be necessary and includes a wetting agent.

Typical Analysis

Ash:	0.2 %
Volatiles:	0.4 %
Moisture:	0.5 %
Fixed Carbon:	98.9 % (on a dry basis)
Sulphur:	0.9 %
Bulk Density:	840 to 1000 kg/m ³
Resistivity:	0.15 Ohm.cm

Metallurgical Coke

Metallurgical coke breeze suitable for standard horizontal or vertical groundbeds (not suitable for boreholes)

Typical Analysis

Ash:	8 %
Volatiles:	1 %
Moisture:	10 %
Fixed Carbon:	90 % (on a dry basis)
Sulphur:	1.2 %
Bulk Density:	500 to 600 kg/m ³
Resistivity:	35 to 55 Ohm.cm